



TU-872 SLK

Core: TU-872 SLK**Prepreg: TU-87P SLK**

TU-872 SLK is based on a high performance modified epoxy FR-4 resin. This material is reinforced with regular woven E-glass and designed with low dielectric constant and low dissipation factor for high speed low loss and high frequency multilayer circuit board application. TU-872 SLK material is suitable for environmental protection lead free process and also compatible with FR-4 processes. TU-872 SLK laminates also exhibit excellent moisture resistance, improved CTE, superior chemical resistance, thermal stability, CAF resistance, and toughness enhanced by an allyl network forming compound.

Applications

- Radio frequency
- Backpanel, High performance computing
- Line cards, Storage
- Servers, Telecom, Base station
- Office Routers

Performance and Processing Advantages

- Excellent electrical properties
- Dielectric constant less than 4.0
- Dissipation factor less than 0.010
- Stable and flat Dk/Df performance
- Compatible with modified FR-4 processes
- Excellent moisture resistance and Lead Free reflow process compatible
- Improved Z-axis thermal expansion
- Anti-CAF capability
- Superior dimensional stability, thickness uniformity and flatness
- Excellent through-hole and soldering reliability

Industry Approvals

- IPC-4101E Type Designation : /29, /99, /101, /126
- IPC-4101E/126 Validation Services QPL Certified
- UL Designation – ANSI Grade: FR-4.0
- UL File Number: E189572
- Flammability Rating: 94V-0
- Maximum Operating Temperature: 130°C

Standard Availability

- Thickness: 0.002" [0.05mm] to 0.062" [1.58mm], available in sheet or panel form
- Copper Foil Cladding: 1/3 to 5 oz for built-up & double sides
- Prepregs: Available in roll or panel form
- Glass Styles: 106, 1080, 3313, 2116 and other prepreg grades are available upon request.





Typical Properties for TU-872 SLK Laminate				
	Typical Values	Conditioning	IPC-4101 /126	
Thermal				
Tg (DMA)	220 °C	E-2/105	> 170°C	
Tg (DSC)	200 °C			
Tg (TMA)	190 °C			
Td (TGA)	340 °C			> 340°C
CTE x-axis	12~15 ppm/°C	E-2/105	N/A	
CTE y-axis	12~15 ppm/°C		N/A	
CTE z-axis	2.3 %		<3.0%	
Thermal Stress, Solder Float, 288°C	> 60 sec	A	> 10 sec	
T260	60 min	E-2/105	> 30 min	
T288	20 min		> 15 min	
T300	5 min		> 2 min	
Flammability	94V-0	E-24/125	94V-0	
Electrical				
Permittivity (RC50%)		E-2/105		
1GHz (SPC method/4291B)	4.0/3.8			< 5.2
5GHz (SPC method)	3.9			-
10GHz (SPC method)	3.8	-	-	
Loss Tangent (RC50%)		E-2/105	< 0.035	
1GHz (SPC method/4291B)	0.008/0.006			
5GHz (SPC method)	0.008			
10GHz (SPC method)	0.009			
Volume Resistivity	> 10 ¹⁰ MΩ·cm	C-96/35/90	> 10 ⁶ MΩ·cm	
Surface Resistivity	> 10 ⁸ MΩ	C-96/35/90	> 10 ⁴ MΩ	
Electric Strength	> 40 KV/mm	A	> 30 KV/mm	
Dielectric Breakdown	> 50 KV	A	N/A	
Mechanical				
Young's Modulus		A	N/A	
Warp Direction	26 GPa			
Fill Direction	24 GPa			
Flexural Strength		A	> 60,000 psi	
Lengthwise	> 60,000 psi			
Crosswise	> 50,000 psi	A	> 50,000 psi	
Peel Strength, 1.0 oz. RTF Cu foil	4~7 lb/in	A	> 4 lb/in	
Water Absorption	0.13 %	E-1 /105+D-24/23	< 0.5 %	

NOTE:

1. Property values are for information purposes only and not intended for specification.
2. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.
3. This product is based on a patent pending technology.

