

PTFE/Woven Fiberglass/Ceramic Filled Laminate For Microwave Printed Circuit Boards

AD1000 is a high dielectric constant substrate that permits circuit miniaturization, compared to traditional low loss materials. It is especially beneficial for power amplifiers, filters, couplers and other components using low impedance lines.

AD1000 is a woven glass reinforced laminate. This allows for Greater Dimensional Stability and Mechanical Robustness than other 10 Dk Products. Its large panel size is also advantageous for “multi-circuits per panel” processing.

AD1000 is considered a “soft substrate” and is relatively insensitive to vibrational stress. This allows miniaturized circuitry without requiring the complicated processing or special handling associated with brittle pure ceramic or ceramic hydrocarbon materials.

AD1000 is compatible with processing used for standard PTFE based printed circuit board substrates. In addition, the low Z-axis thermal expansion provided by the ceramic loading will improve plated through hole reliability, compared to typical PTFE based laminates. The low X-Y thermal expansion provides excellent matching to ceramic chip carriers and other ceramic components.

AD1000 was specifically developed for Miniaturized Circuitry for compact devices (i.e., GPS Receivers), Patch Antennas (where smaller size is required), Satellite Communications Systems, Power Amplifiers (PAs), Low Noise Amplifiers (LNAs), Low Noise Block Downconverters (LNBs), Radar Modules and Manifolds, Aircraft Collision Avoidance Systems (TCAS), and Ground Based Radar Systems.

Features:

- Only Woven Glass Reinforced PTFE/ Ceramic with Dk of 10.2 or greater
- Thermal Conductivity is “Best-in-Class”
- High copper peel strength allows for thinner etched line widths
- Lowest Insertion Loss Available
- Larger Panel Sizes Available
- Low Moisture Absorption
- Excellent CTE Values lead to highly reliability ceramic component attachment and PTH reliability

Benefits:

- Mechanically Robust
- Greater Dimensional Stability than Other 10 Dk Products
- Circuit Miniaturization Leads to Weight Savings
- Heat Dissipation and Management
- Greater Signal Integrity
- Cost-Effective Board Layout and Board Processing
- Low Loss in Humid Environments

Typical Applications:

- Ideal for X-Band and Below
- Radar Modules and Manifolds
- Aircraft Collision Avoidance Systems (TCAS)
- Ground Based Radar Surveillance Systems
- Miniaturized Circuitry & Patch Antennas
- Power Amplifiers (PAs)
- Low Noise Amplifiers (LNAs)

The ARLON logo, consisting of the word "ARLON" in a bold, red, sans-serif font. The letter 'O' is stylized with a white circle inside.

TECHNOLOGY ENABLING INNOVATION

Property	Units	Value	Test Method
1. Electrical Properties			
Dielectric Constant (may vary by thickness)			
@1 MHz	-		IPC TM-650 2.5.5.3
@ 10 GHz	-	10.20	IPC TM-650 2.5.5.5
Dissipation Factor			
@ 1 MHz	-		IPC TM-650 2.5.5.3
@ 10 GHz	-	0.0023	IPC TM-650 2.5.5.5
Temperature Coefficient of Dielectric	-		
TC _{εr} @ 10 GHz (-40-150°C)	ppm/°C	-380	IPC TM-650 2.5.5.5
Volume Resistivity			
C96/35/90	MΩ-cm	1.40x10 ⁹	IPC TM-650 2.5.17.1
E24/125	MΩ-cm	5.36x10 ⁷	IPC TM-650 2.5.17.1
Surface Resistivity			
C96/35/90	MΩ	1.80x10 ⁹	IPC TM-650 2.5.17.1
E24/125	MΩ	3.16x10 ⁸	IPC TM-650 2.5.17.1
Electrical Strength	Volts/mil (kV/mm)	622 (24.5)	IPC TM-650 2.5.6.2
Dielectric Breakdown	kV	>45	IPC TM-650 2.5.6
Arc Resistance	sec	>180	IPC TM-650 2.5.1
2. Thermal Properties			
Decomposition Temperature (Td)			
Initial	°C	>500	IPC TM-650 2.3.41
5%	°C	>500	IPC TM-650 2.3.41
T260	min	>60	IPC TM-650 2.4.24.1
T288	min	>60	IPC TM-650 2.4.24.1
T300	min	>60	IPC TM-650 2.4.24.1
Thermal Expansion, CTE (x,y) 50-150°C	ppm/°C	8, 10	IPC TM-650 2.4.41
Thermal Expansion, CTE (z) 50-150°C	ppm/°C	20	IPC TM-650 2.4.24
% z-axis Expansion (50-260°C)	%		IPC TM-650 2.4.24
3. Mechanical Properties			
Peel Strength to Copper (1 oz/35 micron)			
After Thermal Stress	lb/in (N/mm)	>12 (2.1)	IPC TM-650 2.4.8
At Elevated Temperatures (150°)	lb/in (N/mm)	13.6 (2.4)	IPC TM-650 2.4.8.2
After Process Solutions	lb/in (N/mm)		IPC TM-650 2.4.8
Young's Modulus	kpsi (MPa)		IPC TM-650 2.4.18.3
Flexural Strength (Machine/Cross)	kpsi (MPa)		IPC TM-650 2.4.4
Tensile Strength (Machine/Cross)	kpsi (MPa)	5.1/4.3 (35/30)	IPC TM-650 2.4.18.3
Compressive Modulus	kpsi (MPa)	>425	ASTM D-3410
Poisson's Ratio	-	\	ASTM D-3039
4. Physical Properties			
Water Absorption	%	0.03	IPC TM-650 2.6.2.1
Density, ambient 23°C	g/cm ³	3.20	ASTM D792 Method A
Thermal Conductivity	W/mK	0.81	ASTM E1461
Flammability	class	Meets V0	UL-94
NASA Outgassing, 125°C, ≤10 ⁻⁶ torr	%		NASA SP-R-0022A
Total Mass Loss	%	0.01	NASA SP-R-0022A
Collected Volatiles	%	0.00	NASA SP-R-0022A
Water Vapor Recovered	%	0.00	NASA SP-R-0022A

***Alternative Thickness and Dielectric Constant (Dk) options are available. Tighter tolerances are also available under the AD1001 designation for some thickness. Please discuss your needs with Arlon's Applications Engineering Teams.*

Results listed above are typical properties; they are not to be used as specification limits. The above information creates no expressed or implied warranties. The properties of Arlon laminates may vary, depending on the design and application.

Thickness and Dielectric Constant Alternatives

Thickness (mils)	0.006 ±0.0005	0.0105 ±0.0010	0.015 ±0.0015	0.020 ±0.002	0.025 ±0.002	0.030 ±0.002	0.050 ±0.002	0.059 ±0.003	0.125 ±0.003	0.127 ±0.003
Dielectric Constant	7.8	9.1	9.7	10	10.2	10.35	10.2 or 10.6	10.7	10.2	10.9
Constant	±0.30	±0.35	±0.35	±0.35	±0.35	±0.35	±0.35	±0.35	±0.35	±0.35

* Thicker Options are available. Please Contact Customer Service or your Local Arlon




Figure 1

Demonstrates the Stability of Dielectric Constant across Frequency. This information was correlated from data generated by using a free space and circular resonator cavity. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, thus simplifying the final design process when working across EM spectrum. The stability of the Dielectric Constant of AD1000 over frequency ensures easy design transition and scalability of design.




Figure 2

Demonstrates the Stability of Dissipation Factor across Frequency. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, providing a stable platform for high frequency applications where signal integrity is critical to the overall performance of the application.

Material Availability:

AD1000 laminates are available in a range of thicknesses from 0.020" to 0.127" (and beyond). AD1000 is supplied with 1/2, 1 or 2 ounce standard or reverse treat electrodeposited (ED) copper on both sides. Other copper weights and rolled copper foil are available. AD1000 is available bonded to heavy metal ground planes. Aluminum, brass or copper plates also provide an integral heat sink and mechanical support to the substrate.

Other combinations of thickness and cladding may be available. Contact Arlon with any requests for nonstandard materials. When ordering AD1000, please specify thickness, cladding, panel size, and any other special considerations. Standard panel sizes include: 18" x 24", 12" x 18" and 16" x 18". Contact Arlon Customer Service for other panel sizes.



TECHNOLOGY ENABLING INNOVATION

Arlon Microwave Materials... Challenge Us

For samples, technical assistance, customer service or for more information, please contact Arlon Materials for Electronics Division at the following locations:

NORTH AMERICA:

Arlon, Inc.
Electronic Substrates
9433 Hyssop Drive
Rancho Cucamonga, CA 91730
Tel: (909) 987-9533
Fax: (909) 987-8541

Arlon, Inc.
Microwave Materials
1100 Governor Lea Road
Bear, DE 19701
Tel: (800) 635-9333
Outside U.S. & Canada: (302) 834-2100
Fax: (302) 834-2574

NORTHERN EUROPE:

Arlon, Inc.
44 Wilby Avenue
Little Lever
Bolton, Lancashire BL31QE
United Kingdom
Tel: (44) 120-457-6068
Fax: (44) 120-479-6463

SOUTHERN CHINA:

Arlon, Inc.
Room 601, Unit 1, Bldg 6
Liyuan, Xincun Shahe
Shenzhen, China 518053
Tel: (86) 755-269-066-12
Fax: (86) 755-26910475

NORTHERN CHINA:

Arlon, Inc.
Room 11/401, No. 8
Hong Gu Road
Shanghai, China 200336
Tel/Fax: (86) 21-6209-0202

SOUTHERN EUROPE:

Arlon, Inc.
1 Bis Rue de la Remarde
91530 Saint Cheron, France
Tel: (33) 951-096-082
Fax: (33) 164-566-489